

Product Technical Data

Application:

Treated SureCure[®] is used as a seed crystal to promote consistent formation of tetrabasic lead sulfate during paste mixing and curing. It is suitable for light duty cycle application.

Typical Properties:

Tetrabasic Lead Sulfate Content (4PbO · PbSO₄): 94% typical, 90% minimum (by Rigaku Miniflex)

Median Particle Size: 1.0 micron typical (by Micromeritics Sedigraph 5125)

Moisture Content: 0.3% maximum

Color: White to light yellow

Packaging:

Available in 5 kg, 10 kg, and 24 lbs. bags. Other packaging available upon request.

Usage Instructions:

Treated SureCure[®] should be added to the paste mix at 1% of total oxide weight before the addition of water or acid. This helps to ensure a homogeneous paste mix.

Recommended Curing Profile:

75°C for 48 hrs during high humidity (>95% RH) step. For different curing temperatures and conditions, please contact HGI technical team for consultation.

Impurities:

Element	Maximum w/w%	Typical w/w%
Fe	0.0100	0.0020
Zn	0.0010	0.0001
Cu	0.0015	0.0001
Ag	0.0050	0.0035
Ni	0.0010	0.0001
As	0.0010	0.0001